

Applicant: RAYCHEM ELECTRONICS (SHANGHAI) LTD.
NO.307 QIN JIANG ROAD SHANGHAI P.R CHINA
Attn: SHEN YUE DONG

Date: 14 Dec, 2015

Sample Description:

One(1) group of submitted sample said to be : Black plastic tube
Item Name : ZH4-2.5-0-SP-SM
Lot No. : 201749455

Tests Conducted:


As requested by the applicant, for details refer to attached page(s).

Conclusion:

<u>Tested Sample</u>	<u>Standard</u>	<u>Result</u>
Submitted sample	Restriction of the use of certain hazardous substance in electrical and electronic equipment (RoHS Directive 2011/65/EU)	Pass
Tested component of submitted sample	Halogen (F, Cl, Br, I) content	See Test Conducted
	TBBPA & TBBPA-bis(2,3-dibromopropyl ether) content	See Test Conducted
Tested Component	Dimethylfumarate Content Requirement In Annex XVII Item 61 Of The REACH Regulation (EC) NO. 1907/2006 & Amendment (EU) No. 412/2012	Pass
Tested component of submitted sample	Chlorinated paraffin (C10 - C13) content	See Test Conducted
	Phthalates content requirement in Annex XVII items 51 & 52 of the REACH regulation (EC) NO. 1907/2006 & Amendment NO.552/2009	Pass
	BS EN 71-3:2013+A1:2014 for migration of certain elements	Pass
Tested components of submitted sample	Formaldehyde Content	See Test Conducted
Tested component of submitted sample	PFOS and PFOA content	See test conducted
	NP/OP/NPEO/OPEO content	See test conducted
	Organotin content requirement in Annex XVII item 20 of the Reach regulation (EC) No.1907/2006 & amendent (EU) No.276/2010	Pass
	Asbestos qualitative test	See Test Conducted

To be continued

Authorized By:
For Intertek Testing Services Ltd., Shanghai



Leo Shi
General Manager



Tested Sample

Tested component of submitted sample

Test Item

Qualitative test for Polyvinyl Chloride(PVC)

Result


See test conducted

Regulation (EC) No.1005/2009 Amending Regulation
(EC) No.744/2010 on Ozone Depleting Substance
(ODS) content

See test conducted

To be continued

Authorized By:
For Intertek Testing Services Ltd., Shanghai



Leo Shi
General Manager



Tests Conducted

1 (A) Test result of RoHS Directive:

Testing Item	Result
	(1)
Cadmium (Cd) content (mg/kg)	ND
Lead (Pb) content (mg/kg)	ND
Mercury (Hg) content (mg/kg)	ND
Chromium (VI) (Cr ⁶⁺) content (mg/kg) (for non-metal)	ND
Polybrominated biphenyls (PBBs) (mg/kg)	
monobromo biphenyls (MonoBB)	ND
Dibromo biphenyls (DiBB)	ND
Tribromo biphenyls (TriBB)	ND
Tetrabromo biphenyls (TetraBB)	ND
Pentabromo biphenyls (PentaBB)	ND
Hexabromo biphenyls (HexaBB)	ND
Heptabromo biphenyls (HeptaBB)	ND
Octabromo biphenyls (OctaBB)	ND
Nonabromo biphenyls (NonaBB)	ND
Decabromo biphenyl (DecaBB)	ND
Polybrominated diphenyl ethers (PBDEs) (mg/kg)	
Monobromo diphenyl ethers (MonoBDE)	ND
Dibromo diphenyl ethers (DiBDE)	ND
Tribromo diphenyl ethers (TriBDE)	ND
Tetrabromo diphenyl ethers (TetraBDE)	ND
Pentabromo diphenyl ethers (PentaBDE)	ND
Hexabromo diphenyl ethers (HexaBDE)	ND
Heptabromo diphenyl ethers (HeptaBDE)	ND
Octabromo diphenyl ethers (OctaBDE)	ND
Nonabromo diphenyl ethers (NonaBDE)	ND
Decabromo diphenyl ether (DecaBDE)	ND

Remark: ND = Not Detected

Tested Component: See component list in the last section of this report.

To be continued

Tests Conducted

(B) RoHS Requirement:

Restricted Substances	Limits
Cadmium (Cd)	0.01% (100 mg/kg)
Lead (Pb)	0.1% (1000 mg/kg)
Mercury (Hg)	0.1% (1000 mg/kg)
Chromium (VI) (Cr ⁶⁺)	0.1% (1000 mg/kg)
Polybrominated biphenyls (PBBs)	0.1% (1000 mg/kg)
Polybrominated diphenyl ethers (PBDEs)	0.1% (1000 mg/kg)

The above limits were quoted from RoHS Directive 2011/65/EU for homogeneous material.

(C) Test method:

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd) content	With reference to IEC 62321-5 Edition 1.0: 2013, by acid digestion until the tested sample was totally dissolved, and determined by ICP-OES.	2 mg/kg
Lead (Pb) content	With reference to IEC 62321-5 Edition 1.0: 2013, by acid digestion until the tested sample was totally dissolved, and determined by ICP-OES.	2 mg/kg
Mercury (Hg) content	With reference to IEC 62321-4 Edition 1.0: 2013, by acid digestion until the tested sample was totally dissolved, and determined by ICP-OES.	2 mg/kg
Chromium (VI) (Cr ⁶⁺) content (for non-metal)	With reference to IEC 62321 Edition 1.0: 2008, by alkaline digestion and determined by UV-VIS Spectrophotometer.	1mg/kg
Polybrominated biphenyls (PBBs)& polybrominated diphenyl ethers (PBDEs)	With reference to IEC 62321 Edition 1.0: 2008, by solvent extraction and determined by GC/MS and further HPLC confirmation when necessary.	5 mg/kg

Date sample received : Dec.2, 2015


Testing period : Dec.2, 2015 to Dec.7, 2015

To be continued


Tests Conducted

(D) Measurement flowchart:

1. Test for Cd/Pb Contents




2. Test for Hg Content




To be continued

Tests Conducted

3. Test for Chromium (VI) (Cr^{6+}) Content (Alkaline Digestion)




4. Test for Chromium (VI) (Cr^{6+}) Content (Boiling Water Extraction)




To be continued

Tests Conducted

5. Test for PBBs/PBDEs Contents



6. Test for Phthalate Contents



To be continued

Tests Conducted

2 Detection Of Amines Derived From Azocolourants and Azodyes:

By Gas Chromatographic - Mass Spectrometric (GC-MS) and High Performance Liquid Chromatographic (HPLC) analysis.

Test Method: EN 14362-1: 2012 for Textile Material
EN ISO 17234-1: 2010 for Leather Material
EN 14362-3: 2012 & EN ISO 17234-2: 2011 for p-Aminoazobenzene

	<u>Forbidden</u>	<u>Cas No.</u>	<u>Result</u> (1)
1.	4-Aminodiphenyl	92-67-1	ND
2.	Benzidine	92-87-5	ND
3.	4-Chloro-o-Toluidine	95-69-2	ND
4.	2-Naphthylamine	91-59-8	ND
5.	o-Aminoazotoluene	97-56-3	ND
6.	2-Amino-4-Nitrotoluene	99-55-8	ND
7.	p-Chloroaniline	106-47-8	ND
8.	2,4-Diaminoanisole	615-05-4	ND
9.	4,4'-Diaminodiphenylmethane	101-77-9	ND
10.	3,3'-Dichlorobenzidine	91-94-1	ND
11.	3,3'-Dimethoxybenzidine	119-90-4	ND
12.	3,3'-Dimethylbenzidine	119-93-7	ND
13.	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	ND
14.	p-Cresidine	120-71-8	ND
15.	4,4'-Methylene-Bis(2-Chloroaniline)	101-14-4	ND
16.	4,4'-Oxydianiline	101-80-4	ND
17.	4,4'-Thiodianiline	139-65-1	ND
18.	o-Toluidine	95-53-4	ND
19.	2,4-Toluylenediamine	95-80-7	ND
20.	2,4,5-Trimethylaniline	137-17-7	ND
21.	o-Anisidine	90-04-0	ND
22.	p-Aminoazobenzene	60-09-3	ND
23.	2,4-Xylidine	95-68-1	ND
24.	2,6-Xylidine	87-62-7	ND

Remark: ND = Not Detected
Detection Limit = 5 ppm
Requirement = Not Used (Less than 20ppm)
ppm = Parts per million = mg/kg

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.5, 2015

To be continued

Tests Conducted

3 Tested Components: See component list in the last section of this report.

Halogen Test

I . Test result summary

Halogen content :

Testing Item	Result (ppm)
	(1)
Fluorine (F) content	ND
Chlorine (Cl) content	ND
Bromine (Br) content	ND
Iodine (I) content	ND

Remark: ppm = Parts per million = mg/kg
ND = Not Detected

II . Test method

Testing Item	Testing Method	Reporting Limit
Halogen (F, Cl, Br, I) content	With reference to EN 14582:2007 by combustion in a calorimetric bomb and determined by ion chromatography	50 ppm

Remarks: Reporting limit = Quantitation limit of analyte in sample

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.10, 2015


To be continued

Tests Conducted

(III) Measurement flowchart:

Test for Halogen content

Reference method: EN 14582: 2007



To be continued

Tests Conducted

4 TBBPA-bis and TBBPA

(I) Test result summary:

<u>Testing Item</u>	<u>Result (ppm)</u>
	(1)
TBBPA-bis(2,3-dibromopropyl ether) (Tetrabromobisphenol A –bis (2,3-dibromopropyl ether))	ND
TBBPA (Tetrabromobisphenol A)	ND

Remarks: ppm = Parts per million = mg/kg

ND = Not Detected

(II) Test method:

<u>Testing Item</u>	<u>Testing Method</u>	<u>Reporting Limit</u>
TBBPA-bis(2,3-dibromopropyl ether) (Tetrabromobisphenol A –bis(2,3-dibromopropyl ether))	With reference to US EPA 3540C, by solvent extraction and determined by HPLC	10 ppm
TBBPA (Tetrabromobisphenol A)	With reference to USEPA 3540C, by solvent extraction and determined by GC/MS	10 ppm

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015


Testing period : Dec.2, 2015 to Dec.10, 2015

To be continued

Tests Conducted

Measurement flowchart

Test for **TBBPA** content:



To be continued

Tests Conducted

5 Dimethyl Fumarate Content

By Solvent Extraction And Gas Chromatographic-Mass Spectrometric (GC-MS) Analysis.

<u>Tested Component</u> (1)	<u>Result (ppm)</u> <0.05	<u>Requirement (ppm)</u> 0.1
--------------------------------	------------------------------	---------------------------------

Remark: Detection Limit = 0.05ppm
ppm = parts per million = mg/kg

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.7, 2015

6 Chlorinated Paraffin (C10 - C13)

By solvent extraction and Gas Chromatography analysis using Mass Spectrometry or Electron Capture Detector.

<u>Tested Component</u> (1)	<u>Result (% w/w)</u> ND
--------------------------------	-----------------------------

Remark: Detection Limit = 0.01%(w/w)
ND = Not Detected

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.7, 2015

To be continued

Tests Conducted

7 Detection of Polycyclic Aromatic Hydrocarbons (PAHs)

As per the document ZEK 01.4-08 issued by the central experience exchange office (ZEK), by solvent extraction and determined by GC-MSD.

Compound	Result (ppm)	Requirement (ppm)
	(1)	
Naphthalene	0.4	--
Acenaphthylene	ND	--
Acenaphthene	ND	--
Fluorene	ND	--
Phenanthrene	0.3	--
Anthracene	ND	--
Fluoranthene	ND	--
Pyrene	0.3	--
Chrysene	ND	--
Benzo[a]anthracene	ND	--
Benzo[b]fluoranthene	ND	--
Benzo[k]fluoranthene	ND	--
Benzo[a]pyrene	ND	1 (max.)
Dibenzo[a,h]anthracene	ND	--
Indeno[1,2,3-cd]pyrene	ND	--
Benzo[g,h,i]perylene	ND	--
Benzo[j]fluoranthene	ND	
Benzo[e]pyrene	ND	
Sum:	1.0	10 (max.)

Remark: ND = Not Detected
ppm = Parts per million = mg/kg
Detection Limit = 0.2 ppm

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.7, 2015

To be continued

Tests Conducted

8 Phthalate content test

With reference to EN 14372, by Gas Chromatography-Mass Spectrometry (GC-MS) analysis.

<u>Tested compound</u>	<u>Result (% w/w)</u>	<u>Limit(% w/w)</u> <u>(MAX.)</u>
	(1)	
Di-butyl phthalate (DBP)	ND	---
Di(2-ethyl hexyl) phthalate(DEHP)	ND	---
Benzyl butyl phthalate (BBP)	ND	---
Sum of three phthalates	ND	0.1
Di-iso-nonyl phthalate (DINP)	ND	---
Di-n-octyl phthalate (DNOP)	ND	---
Di-iso-decyl phthalate (DIDP)	ND	---
Sum of three phthalates	ND	0.1

Remark: The above limit was quoted according to Annex XVII items 51 & 52 of the REACH regulation (EC) NO.1907/2006 & Amendment NO.552/2009 for phthalate content in toys and children care articles.

Detection limit = 0.01%(w/w)
ND = Not detected

Tested components: See component list in the last section of this report.

Date sample received : Dec.2, 2015


Testing period : Dec.2, 2015 to Dec.6, 2015

To be continued

Tests Conducted

Measurement flowchart:

Test for phthalate content



To be continued

Tests Conducted

9 19 Toxic Elements Migration Test

(A) Test Result

As per BS EN 71-3: 2013 + A1:2014 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography-Inductively Coupled Plasma-Mass Spectrometry, and Gas Chromatographic - Mass Spectrometry.

Category (III): Scraped-off toy material

<u>Element</u>	<u>Result (mg/kg)</u> (1)	<u>Limit (mg/kg)</u>
Aluminium (Al)	< 300	70000
Antimony (Sb)	< 10	560
Arsenic (As)	< 10	47
Barium (Ba)	< 10	18750
Boron (B)	< 50	15000
Cadmium (Cd)	< 5	17
Chromium (III) (Cr III)	< 10	460
Chromium (VI) (Cr VI)	< 0.2	0.2
Cobalt (Co)	< 10	130
Copper (Cu)	< 10	7700
Lead (Pb)	< 10	160
Manganese (Mn)	< 10	15000
Mercury (Hg)	< 10	94
Nickel (Ni)	< 10	930
Selenium (Se)	< 10	460
Strontium (Sr)	< 100	56000
Tin (Sn)	< 10	180000
Organic tin	< 3.0	12
Zinc (Zn)	699	46000

Remark: mg/kg = milligram per kilogram

- Organic tin test result was expressed as tributyl tin.

- Unless specified, determination of Chromium (III), Chromium (VI) and Organic tin was based on elemental analysis.

Tested Components: See component list in the last section of this report.

(B) Categories of various toy materials

Category I: Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II: Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

To be continued

Tests Conducted

Category III: Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.7, 2015

10 Formaldehyde Content

As per test method EN ISO 17226-2, formaldehyde content was determined by UV- Visible Spectrophotometer(UV-Vis) analysis.

<u>Tested Component</u>	<u>Result (mg/kg)</u>
(1)	ND

Remark: ND = Not Detected
Detection Limit = 5.0 mg/kg

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.10, 2015

11 Perfluorooctane Sulfonates (PFOS) And Perfluorooctanoic Acid (PFOA) Content

By solvent extraction and followed by Liquid Chromatography-Mass Spectrometry (LC-MS) analysis.

<u>Compound</u>	<u>Result (ppm)</u>
	(1)
Perfluorooctane sulfonates(PFOS)#	ND
Perfluorooctanoic acid(PFOA)	ND

Remark: Detection Limit = 0.1ppm
ppm = Parts per million = mg/kg
ND = Not Detected
= The reported value was calculated by summation of the values of Perfluorooctanesulfonic Acid, Perfluorooctanesulfonamide, N-Methyl-Perfluorooctanesulfonamide, N-Ethyl-Perfluorooctanesulfonamide, N-Methyl-Perfluorooctanesulfonamidoethanol and N-Ethyl-Perfluorooctanesulfonamidoethanol.

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015


Testing period : Dec.2, 2015 to Dec.7, 2015

To be continued

Tests Conducted

Measurement flowchart:

Test for **Perfluorooctane Sulfonates(PFOS)**and **Perfluorooctanoic Acid (PFOA)** content:



To be continued

Tests Conducted
12 Nonylphenol (NP), Octylphenol (OP), Nonylphenol Ethoxylates(NPEO)and Octylphenol Ethoxylates (OPEO) Content

By solvent extraction and followed by Liquid Chromatographic - Mass Spectrometric (LC-MS) analysis.

<u>Compound</u>	<u>Result (ppm)</u>
	(1)
NP	<10
OP	<10
NPEO	<10
OPEO	<10

Remark: Detection Limit = 10 ppm
ppm = Parts per million = mg/kg

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.7, 2015

13 Organotin Content

By solvent extraction, followed by Gas Chromatography - Mass Spectrometry (GC-MS) analysis.

<u>Compound</u>	<u>Result (%. w/w) of tin</u>	<u>Requirement (%. w/w) of tin</u>
	(1)	
Tri-substituted Organotin [@]	<0.001	0.1
Dibutyl tin (DBT)	<0.001	0.1
Diocetyl tin (DOT)	<0.001	0.1

Remark: The above requirement was quoted according to Annex XVII item 20 of the Reach regulation (EC) No.1907/2006 & amendent (EU) No.276/2010 for organotin content.

Remarks: Detection Limit = 0.001% (w/w) of tin
[@] = The reported value was calculated by summation of the values of Tri-butyltin, Tri-phenyltin, Tri-methyltin, Tri-octyltin, Tri-cyclohexyltin

Tested Components: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.10, 2015

To be continued

Tests Conducted

14 Polychlorinated biphenyls (PCBs)

By solvent extraction and Gas Chromatography-Mass Spectrometry (GC-MS) or Electron Capture Detector (GC-ECD) analysis.

Compound determined: PCB-28, PCB -52, PCB -101, PCB -153, PCB -138, PCB -180

<u>Tested Component</u> (1)	<u>Result(Total) (ppm)</u> ND	<u>Requirement (ppm)</u> Not used(<1.0ppm)
--------------------------------	----------------------------------	---

Remark: Detection Limit = 0.5ppm
ppm = Parts per million = mg/kg
ND = Not Detected

Tested Component: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.7, 2015

15 Asbestos

As per test method NIOSH 9002, Asbestos qualitative test was determined by microscopic examination method.

<u>Tested Component</u> (1)	<u>Result</u> negative
--------------------------------	---------------------------

Analyte: Actinolite, Amosite, Crocidolite, Tremolite, Anthophyllite, Chrysotile

Tested Component: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.7, 2015

16 Qualitative Test For Polyvinyl Chloride(PVC)

With solvent extraction,by Fourier Transform Infrared spectrometer(FTIR) test.

Result: Polyvinyl Chloride (PVC) was not detected on tested component(1) of the submitted sample.


Tested Component: See component list in the last section of this report.

Date sample received : Dec.2, 2015
Testing period : Dec.2, 2015 to Dec.10, 2015

To be continued

Tests Conducted

Determination Of PVC Flow Chart



To be continued

Tests Conducted

17 Detection of Ozone Depleting Substance (ODS)

With reference to US EPA 5021A / 8260C and determined by Headspace - Gas Chromatography Mass Spectrometric (HS - GC/MS) analysis.

<u>Test Item</u>	<u>Result (mg/kg)</u>
Chlorofluorocarbon (CFCs) (Group I)	ND
Halon (Group II)	ND
Carbon Tetrachloride (CCl ₄)(Group IV)	ND
1,1,1-Trichloroethane (Group V)	ND
Bromomethane (Group VI)	ND
Hydrochlorofluorocarbon (HCFCs) (Group VIII)	ND

Remark: Details of Group I to Group IX Ozone Depleting Chemicals are listed in annex I

ND = Not Detected

Detection limit = 1 mg/kg

Tested Component(s): See component list in the last section of this report.

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.7, 2015

To be continued

Tests Conducted

Annex I
Group I to Group IX Ozone Depleting Chemicals (ODC'S)

As listed in annex 1 of Regulation (EC) No. 1005/2009 of The European Parliament and of The Council of 16 September 2009 on substances that deplete the ozone layer.

Group	Substance	
Group I	CFCI ₃ (CFC-11) CF ₂ Cl ₂ (CFC-12) C ₂ F ₃ Cl ₃ (CFC-113)	C ₂ F ₄ Cl ₂ (CFC-114) C ₂ F ₅ Cl (CFC-115)
Group II	CF ₃ Cl (CFC-13) C ₂ FCl ₅ (CFC-111) C ₂ F ₂ Cl ₄ (CFC-112) C ₃ FCl ₇ (CFC-211) C ₃ F ₂ Cl ₆ (CFC - 212)	C ₃ F ₃ Cl ₅ (CFC - 213) C ₃ F ₄ Cl ₄ (CFC - 214) C ₃ F ₅ Cl ₃ (CFC - 215) C ₃ F ₆ Cl ₂ (CFC - 216) C ₃ F ₇ Cl (CFC - 217)
Group III	CF ₂ ClBr (Halon - 1211) CF ₃ Br (Halon - 1301)	C ₂ F ₄ Br ₂ (Halon - 2402)
Group IV	CCl ₄ (Carbon Tetrachloride)	
Group V	C ₂ H ₃ Cl ₃ (1,1,1-Trichloroethane)	
Group VI	CH ₃ Br (Methyl Bromide)	
Group VII	CHFBr ₂ CH ₂ FBr C ₂ HF ₂ Br ₃ C ₂ HF ₄ Br C ₂ H ₂ F ₂ Br ₂ C ₂ H ₃ FBr ₂ C ₂ H ₄ FBr C ₃ HF ₂ Br ₅ C ₃ HF ₄ Br ₃ C ₃ HF ₅ Br ₂ C ₃ H ₂ FBr ₅ C ₃ H ₂ F ₄ Br ₂ C ₃ H ₃ FBr ₄ C ₃ H ₃ F ₃ Br ₂ C ₃ H ₄ FBr ₃ C ₃ H ₄ F ₃ Br C ₃ H ₅ F ₂ Br	CHF ₂ Br C ₂ HFBr ₄ C ₂ HF ₃ Br ₂ C ₂ H ₂ FBr ₃ C ₂ H ₂ F ₃ Br C ₂ H ₃ F ₂ Br C ₃ HFBr ₆ C ₃ HF ₃ Br ₄ C ₃ HF ₆ Br C ₃ H ₂ F ₂ Br ₄ C ₃ H ₂ F ₃ Br ₃ C ₃ H ₂ F ₅ Br C ₃ H ₃ F ₂ Br ₃ C ₃ H ₃ F ₄ Br C ₃ H ₄ F ₂ Br ₂ C ₃ H ₅ FBr ₂ C ₃ H ₆ FBr
Group VIII	CHFCl ₂ (HCFC - 21) CHF ₂ Cl (HCFC - 22) CH ₂ FCI (HCFC - 31) C ₂ HFCl ₄ (HCFC - 121) C ₂ HF ₂ Cl ₃ (HCFC - 122) C ₂ HF ₃ Cl ₂ (HCFC - 123) C ₂ HF ₄ Cl (HCFC - 124) C ₂ H ₂ FCI ₃ (HCFC - 131) C ₂ H ₂ F ₂ Cl ₂ (HCFC - 132) C ₂ H ₂ F ₃ Cl (HCFC - 133) C ₂ H ₃ FCI ₂ (HCFC - 141) C ₂ H ₃ CFCl ₂ (HCFC - 141b) C ₂ H ₃ F ₂ Cl (HCFC - 142) CH ₃ CF ₂ Cl (HCFC - 142b) C ₂ H ₄ FCI (HCFC - 151) C ₃ HFCI ₆ (HCFC - 221) C ₃ HF ₂ Cl ₅ (HCFC - 222) C ₃ HF ₃ Cl ₄ (HCFC - 223)	C ₃ HF ₅ Cl ₂ (HCFC - 225) CF ₃ CF ₂ CHCl ₂ (HCFC - 225ca) CF ₂ CICF ₂ CHCICF (HCFC - 225cb) C ₃ HF ₆ Cl (HCFC - 226) C ₃ H ₂ FCI ₅ (HCFC - 231) C ₃ H ₂ F ₂ Cl ₄ (HCFC - 232) C ₃ H ₂ F ₃ Cl ₃ (HCFC - 233) C ₃ H ₂ F ₄ Cl ₂ (HCFC - 234) C ₃ H ₂ F ₅ Cl (HCFC - 235) C ₃ H ₃ FCI ₄ (HCFC - 241) C ₃ H ₃ F ₂ Cl ₃ (HCFC - 242) C ₃ H ₃ F ₃ Cl ₂ (HCFC - 243) C ₃ H ₃ F ₄ Cl (HCFC - 244) C ₃ H ₄ FCI ₃ (HCFC - 251) C ₃ H ₄ F ₂ Cl ₂ (HCFC - 252) C ₃ H ₄ F ₃ Cl (HCFC - 253) C ₃ H ₅ FCI ₂ (HCFC - 261) C ₃ H ₅ F ₂ Cl (CFC - 262)
Group VIII		

Test Report

Number: SHAH00627969

Tests Conducted

Group

Substance

C₃HF₄Cl₃ (HCFC - 224)

C₃H₆FCI (CFC - 271)

Group IX

CH₂BrCl (halon 1011 bromochloromethane)

18 Flame Retardants

By solvent extraction, followed by Gas Chromatography Mass Spectrometric (GC/MS) and Liquid Chromatography Mass Spectrometric (LC/MS) analysis.

Test item	CAS No	Result (mg/kg)	Reporting limit (mg/kg)
		Tested component	
		(1)	
Polychlorinated naphthalenes (PCNs)	--	ND	5

ND = Not Detected



Picture of sample

Date sample received : Dec.2, 2015

Testing period : Dec.2, 2015 to Dec.7, 2015

Components List:

(1) Black plastic tube

End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.